

**Test report of a National
Cables Industry
CU/XLPE/AWA/LSF
BS 6724 1x70mm² cable
to BS EN 50266-2-4:2001**


Prepared for:
BASEC
23 Presley Way
Crownhill
Milton Keynes
MK8 0ES

21 January 2011

Test report number 268193-2



0578



Prepared on behalf of BRE Global by

Name Ewan MacDonald

Position Consultant

Signature

Approved on behalf of BRE Global by

Name Dave Hoare

Position Senior Consultant

Date 21 January 2011

Signature

BRE Global
Bucknalls Lane
Watford
Herts
WD25 9XX
T + 44 (0) 1923 664100
F + 44 (0) 1923 664994
E enquiries@breglobal.com
www.breglobal.com


BRE Global is not UKAS accredited to make opinions and interpretation. Any opinions and interpretations included as part of this report are clearly marked as such.



0578

This report may only be distributed in its entirety and in accordance with the terms and conditions of the contract. Test results relate only to the items tested. We have no responsibility for the design, materials, workmanship or performance of the product or items tested. This report does not constitute an approval, certification or endorsement of the product tested.

This report is made on behalf of BRE Global. By receiving the report and action on it, the client accepts that no individual is personally liable in contract, tort or breach of statutory duty (including negligence). No third party has any right to rely on this report.



Executive Summary

BASEC Order number: D5TTP558

BASEC Client: National Cables Industry, P.O. Box 27472, Al Dhaid Road, Al Sajja Industrial Area, Sharjah,
United Arab Emirates


Product: CU/XLPE/AWA/LSF BS 6724 1x70mm²

Test Undertaken: BS EN 50266-2-4:2001

Performance requirement: Extent of char no greater than 2.50m above the base of the gas burner.

Measured performance: 0.55m


Conclusion: The cable satisfied the performance requirement in Annex B of BS EN 50266-2-4:2001



1 Introduction

The requirement of the work was to determine the performance of a cable when it is subjected to the conditions specified in BS EN 50266-2-4:2001, 'Common test methods for cables under fire conditions - Tests for vertical flame spread of vertically-mounted bunched wires or cables – Part 2-4: Procedures – Category C' [1].

The client for this work was BASEC, Milton Keynes, UK. The client's order number was D5TTP558.



2 Details of sample received and test carried out

The cable tested was a 22.7mm diameter, single core cable comprising 1 off 70mm² insulated stranded copper conductor, bedding, wire armour and a black over sheath. The over sheath had 2 lines of the following embossed marking:

'ELECTRIC CABLE 600/1000V – 1X70 MM2 CU/XLPE/AWA/LSF - BS 6724 NATIONAL CABLES INDUSTRY, U.A.E., 2010'

No material product information was supplied.


The cable manufacturer was National Cables Industry, P.O. Box 27472, Al Dhaid Road, Al Sajja Industrial Area, Sharjah, United Arab Emirates.

The test specimen was supplied by the client and received on 4 January 2011. BRE Global was not involved in the sample selection process and therefore cannot comment upon the relationship between samples supplied for test and the product supplied to market.

The test was conducted on 5 January 2011. Prior to the test being carried out, the cable specimen was conditioned at a temperature of 20°C ±10°C for a period of at least 16 hours.

The test was conducted and reported in accordance with the procedure specified in BS EN 50266-2-4:2001, and this report should be read in conjunction with it.

A single 20 kW gas burner was used with a flame application time of 20 minutes.



3 Determination of the cable quantity

The non-metallic volume of the cable, calculated as defined in BS EN 50266-2-4:2001, was found to be 0.2479 l/m.


The client required the cable to be tested to Category C, for which BS EN 50266-2-4:2001 defines a non-metallic volume for the cable of 1.5 l/m. Therefore 6 lengths of cable were tested.

The cables were fixed to a 500 mm wide ladder. The cable's diameter required a single layer of 6 cables fixed across the centre of the ladder.

4 Test result

The gas burner was switched off after 20 minutes. All flaming ceased 13 minutes later (33 minutes after the start of the test).

The maximum extent of charring on the sample, measured after the test, was 0.55m above the bottom edge of the burner.



5 Conclusion

The recommended performance criteria given in Annex B of BS EN 50266-2-4:2001 is as follows:

'The maximum extent of the charred portion measured on the sample shall not have reached a height exceeding 2.5 m above the bottom edge of the burner'.

Therefore the National Cables Industry CU/XLPE/ASWA/LSF BS 6724 1x70mm² cable satisfied the recommended performance criteria of BS EN 50266-2-4:2001.

6 Reference

- 1 BS EN 50266-2-4:2001, 'Common test methods for cables under fire conditions - Tests for vertical flame spread of vertically-mounted bunched wires or cables – Part 2-4: Procedures – Category C', British Standards Institution, London, 2001.

=====REPORT ENDS=====